

EAST Search History

Ref #	Hits	Search Query	DBs	Default Operator	Plurals	Time Stamp
L1	573	wafer and protective adj tape	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 05:55
L2	0	1 and die adj bond\$4 with press\$4 with laminat\$3	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 05:55
L3	3	1 and die adj bond\$4 same press\$4 same laminat\$3	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 05:56
L4	6	1 and die adj bond\$4 and press\$4 same laminat\$3	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:01
L5	1	4 and separator adj film	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 05:57
L6	4	4 and grind\$4	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 05:57
L7	4	6 and dic\$4	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 05:58
L8	4	6 and (heat\$4 or temperature or anneal\$4)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 05:59

EAST Search History

L9	968	438/459.ccls.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:00
L10	856	438/458.ccls.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:00
L11	984	438/460.ccls.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:00
L12	247	438/461.ccls.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:00
L13	770	438/462.ccls.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:00
L14	157	438/463.ccls.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:00
L15	1291	438/464.ccls.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:00
L16	629	438/465.ccls.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:00

EAST Search History

L17	25	9 and protective adj tape	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:00
L18	5	10 and protective adj tape	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:00
L19	29	11 and protective adj tape	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:00
L20	0	12 and protective adj tape	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:00
L21	13	13 and protective adj tape	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:00
L22	10	14 and protective adj tape	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:00
L23	46	15 and protective adj tape	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:01
L24	11	16 and protective adj tape	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:01

EAST Search History

L25	1	17 and die adj bond\$4 and press\$4 same laminat\$3	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:01
L26	0	18 and die adj bond\$4 and press\$4 same laminat\$3	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:01
L27	1	19 and die adj bond\$4 and press\$4 same laminat\$3	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:02
L28	0	20 and die adj bond\$4 and press\$4 same laminat\$3	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:02
L29	0	21 and die adj bond\$4 and press\$4 same laminat\$3	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:02
L30	0	22 and die adj bond\$4 and press\$4 same laminat\$3	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:03
L31	0	23 and die adj bond\$4 and press\$4 same laminat\$3	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:03
L32	0	24 and die adj bond\$4 and press\$4 same laminat\$3	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:03

EAST Search History

L33	1	17 and bond\$4 and press\$4 same laminat\$3	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:03
L34	0	18 and bond\$4 and press\$4 same laminat\$3	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:03
L35	1	19 and bond\$4 and press\$4 same laminat\$3	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:04
L36	0	20 and bond\$4 and press\$4 same laminat\$3	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:04
L37	0	21 and bond\$4 and press\$4 same laminat\$3	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:04
L38	0	22 and bond\$4 and press\$4 same laminat\$3	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:04
L39	0	23 and bond\$4 and press\$4 same laminat\$3	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:04
L40	0	24 and bond\$4 and press\$4 same laminat\$3	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:05

EAST Search History

L41	529	protective adj (tape or film) and bond\$4 and press\$4 and laminat\$3 and grind\$4	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:06
L42	91	41 and wafer and grind\$4 and peel\$4	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:05
L43	78	protective adj (tape or film) and bond\$4 same press\$4 same laminat\$3 and grind\$4	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:06
L44	78	protective adj (tape or film) and bond\$4 same press\$4 same laminat\$3 and grind\$4 and (heat\$4 or anneal\$4 or temperature)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:08
L45	69011	Yoshiyuki.in.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:09
L46	4	45 and wafer and protective adj tape	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/06/12 06:09